

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : A61K 7/032	A2	(11) International Publication Number: WO 98/18431 (43) International Publication Date: 7 May 1998 (07.05.98)
(21) International Application Number: PCT/US97/19786 (22) International Filing Date: 30 October 1997 (30.10.97) (30) Priority Data: 08/740,578 31 October 1996 (31.10.96) US (71) Applicant: THE PROCTER & GAMBLE COMPANY [US/US]; One Procter & Gamble Plaza, Cincinnati, OH 45202 (US). (72) Inventors: ALWATTAI, Ali, Abdelaziz; 9325 Winton Road #7, Cincinnati, OH 45231 (US). BARTHOLOMEY, Ed- ward, Martin; 9031 Fieldchat Road, Baltimore, MD 21236 (US). SMITH, Edward, Dewey, III; 6880 Man-O-War Lane, Mason, OH 45040 (US). TARANTINO, David, Ed- mund; 4 Rainflower Path #304, Sparks, MD 21152 (US). WALLING, David, William; 2 Andrews Court, Parkton, MD 21120 (US). (74) Agents: REED, T., David et al.; The Procter & Gamble Company, 5299 Spring Grove Avenue, Cincinnati, OH 45217 (US).		(81) Designated States: AU, CA, CN, CZ, JP, MX, European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>Without international search report and to be republished upon receipt of that report.</i>
(54) Title: COSMETIC COMPOSITIONS COMPRISING AN INSOLUBLE POLYMER, A FILM-FORMING POLYMER AND AN ORGANOPHILIC CLAY		
(57) Abstract The present invention relates to oil-in-water mascara compositions comprising water-insoluble polymeric materials in the form of an aqueous emulsion, water-soluble, film-forming polymers and organophilic clays. Said compositions exhibit improved wear and are removable with soap and water.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakhstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

COSMETIC COMPOSITIONS COMPRISING AN INSOLUBLE POLYMER, A FILM-FORMING POLYMER AND AN ORGANOPHILIC CLAY

5

TECHNICAL FIELD

The present invention relates to cosmetic compositions, particularly eye make-up compositions, most particularly mascaras, comprising water-insoluble polymeric material in the form of an aqueous emulsion and water-soluble, film-forming polymers. In addition, the compositions herein utilize organophilic clays wherein the clays physically complex with the polymers. This serves to reinforce the film applied to the lashes such that smudging & smearing of the mascara is prevented.

BACKGROUND OF THE DISCLOSURE

Eye make-up compositions, including mascara, are significant products in the cosmetics market. Mascara enhances the beauty of the wearer by coating the eye lashes, or in some instances eyebrows, with color.

15

In spite of their beauty enhancing characteristics, conventional eye make-up preparations have been criticized for their failure to produce the desired effects during long periods of wear. Problems such as staining and smearing, commonly referred to as smudging, and flaking of the mascara from the eyelashes are well known. Even where longevity has been improved, such compositions also are known to be difficult to completely remove from the delicate eye area. An eye makeup composition conceptually having significantly superior wear life, yet, easy removability with soap and water would be very desirable. Furthermore, the mascara should provide beauty benefits, particularly in terms of application benefits to the user.

20

Eye makeup compositions comprising polymeric emulsions in order to eliminate smudging are well known in the art and typically include water-insoluble polymers, also referred to as latexes. Such compositions including eye shadows as disclosed in U.S. Patent 3,639,572, Henrich, issued February 1, 1972; and mascaras as disclosed in U.S. Patent 4,423,031, Murui et al., issued December 27, 1983; and European Patent Application (EPA) 0568035, published November 3, 1993. These compositions include plasticizers or solvents to assist in forming films using said latexes. These compositions are known to contain thickeners to adjust the viscosity of the composition. Said thickeners include water-soluble and water-swellaable polymers, typically known for such use in the cosmetic art.

25

30

A different embodiment of the above concept is disclosed in Patent Cooperation Treaty application WO 94/17775, published August 18, 1994. The invention disclosed therein includes mascara compositions comprising water-based silicone elastomeric latex emulsions as opposed to "water-based" acrylic polymers. Longer wear and durability is attributed to the use of the elastomeric latex as it is more compatible with the rest of the compositional matrix than the acrylic polymers.

35

Other compositions known in the art that avoid combining plasticizers and insoluble-polymers

are exemplified in EPO 0530084, published March 3, 1993. This application discloses compositions comprising a internal phase and a external phase, wherein the external phase contains at least one water-soluble polymer and the internal phase contains at least 50% wax. Said composition may contain other materials routinely used in cosmetic compositions including water-insoluble polymers.

5 L'Oreals patent application, WO 91/12793, published 5/4/94, discloses water-resistant composition for eyelashes containing at least one wax, at least one "consistency" agent, at least one volatile organic solvent and 1-35% (by weight of the composition) of an aqueous solution of at least one water-soluble, film-forming polymer. The level of water-soluble, film-forming polymers is between 0.1% and 55%, and does not contain any emulsifying agents. The processing instructions
10 direct one to disperse the aqueous phase into the oil phase thereby making the composition a water-in-oil emulsion. Furthermore, the "consistency agent" (referred to in the specification as a "stability agent") is selected from the group of organically treated argyles.

Organophilic clays are known for use with organic solvent and oil based systems. The benefits derived from the use of organophilic clays in these systems is three-fold. Organophilic clays provide
15 viscosity, flow control and stability to these solvent-based and oil-based systems. This is similar to the way hydrophilic clay thickeners are used water-based products. For example, organoclay, reaction products of an organic quaternary amine with either hectorite or bentonite clay, are capable of swelling and gelling above mentioned organic-based systems to gel various hydrocarbon and natural oils, solvents and synthetic liquids; see "Controlling Cosmetic Rheology," NL Industries (1985), p6.

20 Included among organic solvent-based and oil solvent-based systems are those which are anhydrous or contain water as the dispersed phase as in water-in-oil emulsion systems. Regardless of which of the organic or oil based system are employed, it is understood that the organophilic clays are dispersed in the lipophilic phase to thicken the viscosity of the oils and the vehicle overall. In this manner, they may also be combined with oil-soluble polymeric or resin materials.

25 Until now, however, nowhere has it been disclosed that non-organic solvent or oil based systems such as oil-in-water emulsions can benefit from the use of organophilic clays. By experimentation and ingenuity, it has been surprisingly found incorporating organophilic clays into oil-in-water cosmetic compositions as disclosed herein provides additional wear and beauty benefits not realized in the art.

30 SUMMARY OF THE INVENTION

The present invention is for mascara compositions, removable with soap and water, that provide surprising beauty and wear benefits as compared to compositions known in the art. These compositions comprise from about 3% to about 60% water-insoluble polymeric material, from about 2% to about 50% water-soluble, film-forming polymers and from about 0.05% to about 20.0%
35 organophilic clays.

Compositions of the present invention can be fabricated in a multitude of forms, such as creams, pastes and solids. All percentages are by weight of the cosmetic composition unless otherwise

indicated. All solutions are on a weight/weight concentration unless otherwise indicated.

DETAILED DESCRIPTION OF THE INVENTION

A. Water-insoluble Polymeric Materials

The mascara composition of the present invention comprises water-insoluble polymeric materials in an aqueous emulsion. Said water-insoluble polymeric materials, disclosed in the art as latexes, are aqueous emulsions or dispersions of polymeric materials comprising polymers formed from monomers, said monomer derivatives, mixtures of said monomers, mixtures of said monomer derivatives, natural polymers and mixtures thereof. Said polymeric material also include chemically modified versions of the above polymers. These water-insoluble polymeric materials of the present invention comprise from about 3% to about 60%; preferably from about 4% to about 40% and most preferably from about 5% to about 30% by weight of the composition.

Water-insoluble polymeric material of the present invention comprise monomers selected from the group consisting of aromatic vinyls, dienes, vinyl cyanides, vinyl halides, vinylidene halides, vinyl esters, olefins and their isomers, vinyl pyrrolidone, unsaturated carboxylic acids, alkyl esters of unsaturated carboxylic acids, hydroxy derivatives of alkyl esters of unsaturated carboxylic acids, amides of unsaturated carboxylic acids, amine derivatives of unsaturated carboxylic acids, glycidyl derivatives of alkyl esters of unsaturated carboxylic acids, olefinic diamines and isomers, aromatic diamines, terephthaloyl halides, olefinic polyols and mixtures thereof. Preferred monomers are selected from the group consisting of aromatic vinyls, dienes, vinyl esters, olefins and their isomers, unsaturated carboxylic acids, alkyl esters of unsaturated carboxylic acids, hydroxy derivatives of alkyl esters of unsaturated carboxylic acids, amides of unsaturated carboxylic acids and mixtures thereof. Most preferred monomers are selected from the group consisting of aromatic vinyls, dienes, vinyl esters, alkyl esters of unsaturated carboxylic acids, hydroxy derivatives of alkyl esters of unsaturated carboxylic acids and mixtures thereof. The polymerization process for making said polymeric material of the present invention is well known in the art. Such processes are disclosed in Kirk Othmer, Encyclopedia of Chemical Technology, Volume 14, "Latex Technology" 3rd Ed. 1981; incorporated herein by reference.

Specific polymeric material useful in the present invention include, but, are not necessarily limited to the Syntran Series (of latexes) from Interpolymer Corporation, for example Syntran 5170, Syntran EX33-1, Syntran EX30-1, and Syntran 5130 (acrylates copolymers formulated with added ammonia, propylene glycol, preservative and surfactant) and Syntran 5002 (styrene/acrylates/methacrylate copolymer formulated with added ammonia, propylene glycol, preservative and surfactant); the Primal Series (acrylic latexes) from Rohm & Hass; Appretan V (styrene/acrylic ester copolymer latexes) from Hoechst; Vinac (polyvinylacetate latex) from Air Products; UCAR latex resin 130 (polyvinylacetate latex) from Union Carbide; Rhodopas A Series (polyvinylacetate latexes) from Rhone Poulenc; Appretan MB, EM, TV (vinyl acetate / ethylene copolymer latexes) from Hoechst; 200 Series (styrene/butadiene copolymer latexes) from Dow

Chemical; Rhodopas SB Series (styrene/butadiene copolymer latexes) from Rhone Poulenc; Witcobond (polyurethane latexes) from Witco; Hycar Series (butadiene/acrylonitrile copolymer latexes) from Goodrich; Chemigum Series (butadiene/acrylonitrile copolymer latexes) from Goodyear; and Neo Cryl (styrene/acrylates/acrylonitrile copolymer latex) from ICI Resins.

5 B. Water-soluble, Film Forming Polymers

In addition to the water-insoluble polymeric material disclosed above, the mascara composition of the present invention comprises water-soluble, film forming polymers. Water-soluble, film-forming polymers are defined herein to mean polymers which are soluble in water, water-cosolvent mixtures, such as ethanol/water, pH adjusted water, and/or tempered solutions of the above to
10 facilitate solubilization of the polymers. Water-soluble, film forming polymers comprise from about 0.1% to about 50%, preferably from about 1% to about 30%, and most preferably from about 1.5% to about 10% of the composition.

The film forming, water-soluble polymers comprise polymers formed from monomers, said monomer derivatives, mixtures of said monomers, mixtures of said monomer derivatives, natural
15 polymers and mixtures thereof. The water-soluble, film forming polymers disclosed herein also include chemically modified versions of the above disclosed polymers. Said monomers are selected from the group consisting of olefin oxides, vinyl pyrrolidone, vinyl esters, vinyl alcohols, vinyl cyanides, oxazilines, carboxylic acids and esters and mixtures thereof. Preferred vinyl pyrrolidone polymers are selected from the group consisting of polyvinylpyrrolidone, vinyl acetate/vinyl pyrrolidone copolymer
20 and mixtures thereof. Preferred polyvinyl esters are selected from the group consisting of vinyl acetate/crotonic acid copolymer, vinyl acetate/crotonic acid/vinyl neodecanoate copolymer and mixtures thereof. Preferred vinyl alcohol polymers are selected from the group consisting of vinyl alcohol/vinyl acetate, vinyl alcohol/poly(alkyleneoxy)acrylate, vinyl alcohol/vinyl acetate/poly-
(alkyleneoxy)acrylate and mixtures thereof. Preferred olefin oxides are selected from the group
25 consisting of polyethylene oxide, polypropylene oxide and mixtures thereof. Preferred polycarboxylic acids and their esters are selected from the group consisting of acrylates, acrylates/octylacrylamide copolymers and mixtures thereof. The preferred oxazilines is polyoxazilines.

Water-soluble, film forming polymers of the present invention comprise natural polymers selected from the group consisting of cellulose derivatives, algin and its derivatives, starch and its
30 derivatives, guar and its derivatives, shellac polymers, and mixtures thereof. Preferred cellulose derivatives are selected from the group consisting of hydroxyethylcellulose, hydroxypropylcellulose, hydroxypropyl methylcellulose, ethylhydroxyethyl cellulose and mixtures thereof.

Specific water-soluble, film-forming polymers useful in the present invention include, but are not necessarily limited to Polyox WSR (polyethyleneoxide polymers) from Union Carbide; Natrosol
35 250 (hydroxyethylcellulose) from Aqualon; Cellosize (hydroxyethylcellulose) from Union Carbide; Airvol (polyvinylalcohol copolymer) from Air Products and Chemicals, preferably all commercially available grades like Airvol 103, Airvol 325, Airvol 540, Airvol 523S; Vinex from Air Products and

Chemicals, preferably all commercially available grades such as Vinex 1003, Vinex 2034, Vinex 2144, Vinex 2019; PEOX (polyethyloxazoline) from Polymer Chemistry Innovations; PVP K Series (polyvinylpyrrolidone) from International Specialty Products; Luviskol K Series (polyvinylpyrrolidone) from BASF; PVP/VA (vinyl acetate/vinyl pyrrolidone copolymer) from International Specialty Products, preferably grades W-735 and S-630; and Gantrez (copolymers of methyl vinyl ether/maleic anhydride) from International Specialty Products; Carboset Series (acrylate copolymer) from BF Goodrich; Resyn Series (vinyl acetate/crotonate copolymers) from National Starch and Chemical Corporation; Versatyl and Dermacryl Series (acrylate/octylacrylamide copolymers) from National Starch and Chemical Corporation.

C. Organophilic Clays

As previously disclosed, organophilic clays are known for use in organic solvent-based and oil-based systems, including anhydrous and water-in-oil mascara compositions. While such a system is known for industrial use, it has not been previously applied to the cosmetic arts; see Tie Lan and Dr. T.J. Pinnavaia (Dept. of Chemistry), CMS Courier, Vol I Issue 8, July 1994 ; "Polymer-Clay Nanocomposite Materials", pp.2-3 disclosing the addition of organophilic clays to nylon-6, improve the tensile strength, modulus, rheology and thermal capacity of plastics used in automobile production. We have found that the application of organophilic clays used in sufficient concentrations within an aqueous-based or oil-in-water emulsions results in providing mascara compositions with surprising results including the formation of a physical complex with the water-insoluble, film-forming polymers in the present invention. This complexing of the clays and film-forming polymers yields a composite film that is reinforced by the organophilic clay and thereby preventing smudging or smearing of the product, especially in the case of mascaras. Additionally, the hydrophobic properties of organophilic clays are transferred to the aqueous-based emulsion, thereby imparting a degree of water-resistance to the product. Therefore, a new set of benefits is realized, different from conventional teachings in the cosmetic industry. And these benefits directly impact the overall stability of the cosmetic film on the substrate resulting in long-wear for the consumer.

The organophilic clays are used at levels from about 0.05% to about 20.0%, preferably 1% to about 10% and most preferably from about 2% to about 5% of the compositions of the present invention. Whether the clay is commercially available or not is not a limitation of the present invention. However, the commercially clays are logically preferred.

Clays are generally considered amorphous and crystalline. Among the amorphous clays are those that belong to the allophane group. Crystalline types of clays include two-layer type clays, three layer-type clays, regular mixed-layer type clays and chain structure type clays; see Grim, R.E. Mineralogy, Second Edition, McGraw-Hill, N.Y., 1968.

Two-layer type clays include those that are equi-dimensional and elongate. Equi-dimensional clays include the kaolinite group of clays. The elongate clays include the halloysite group of clays. Three-layer type clays include expanding lattice clays including equi-dimensional and elongate clays as

well as non-expanding lattice clays. Expanding lattice, equi-dimensional clays include smectite and vermiculite groups of clays. The smectite group of clays consists of montmorillonite, bentonite and saunonite. Expanding lattice, elongate clays include the smectite group of clays consisting of nontronite hectorite and saponite. The non-expanding lattice clays include illite. The regular mixed-layer type
5 clays include the chlorite group of clays. The chain structure types of clays include attapulgite and sepiolite types of clay.

Organophilic clays are formed by modifying the above identified clays with compounds selected from the group consisting of quaternary amines, tertiary amines, amine acetates, imidazolines, amine soaps, fatty sulfates, alkyl aryl sulfonates, amine oxides, ethoxylated alkyl phenols and mixtures
10 thereof. These materials are combined with the above clays under ion-exchange conditions renders the clays organophilic.

Among the preferred organically-modified clays for used as the organophilic clays of the present invention are those selected from the group of montmorillonite, bentonite, hectorite, attapulgite, sepiolite and mixtures thereof. Among these organophilic clays for use in the present invention are
15 the following commercially available ones including :

Bentone 34 (Rheox Corp.) - Quaternium-18 Bentonite;
Tixogel VP (United Catalysts) - Quaternium-18 Bentonite;
Bentone 38 (Rheox Corp.) - Quaternium-18 Hectorite;
Bentone SD-3 (Rheox Corp.) - Dihydrogenated Tallow Benzylmonium Hectorite;
20 Bentone 27 (Rheox Corp.) - Stearalkonium Hectorite;
Tixogel LG (United Catalysts) - Stearalkonium Bentonite;
Claytone 34 (Southern Clay) Quaternium-18 Bentonite;
Claytone 40 (Southern Clay) Quaternium-18 Bentonite;
Claytone AF (Southern Clay) Stearalkonium Bentonite;
25 Claytone APA (Southern Clay) Stearalkonium Bentonite;
Claytone GR (Southern Clay) Quaternium-18/Benzalkonium Bentonite;
Claytone HT (Southern Clay) Quaternium-18/Benzalkonium Bentonite;
Claytone PS (Southern Clay) Quaternium-18/Benzalkonium Bentonite;
Claytone XL (Southern Clay) Quaternium-18 Bentonite; and
30 Vistrol 1265 (Cimbar) - Organophilic Attapulgite.

The above organophilic clays can also be purchased as pre-dispersed organophilic clay in either an oil or an organic solvent. The materials are in the form of a heavy paste that can be readily dispersed into the formulation. Such materials include Mastergels by Rheox, United Catalysts, and Southern Clay.

35 The compositions of this invention contain an effective amount of "activator" for the organically modified hectorite and bentonite clays. Many such activators are known in the art, including for example, propylene carbonate, ethanol, and mixtures thereof. The preferred

activator for use is propylene carbonate. Preferably, the ratio of clay to activator is about 3:1.

Optional Ingredients

Optional ingredients useful in the present invention are selected based on either the various forms or attributes the composition is to have. The most preferred embodiments of the present invention are oil-in-water emulsions. Some of the most common optional ingredients include oils and fats, emulsifiers, waxes, pigments and mixtures thereof.

A. Oils and Fats

Mascara compositions of the present invention include oil-in-water emulsion compositions. These compositions require a lipophilic material which forms the internal phase of the composition. Said lipophilic materials typically comprise oils and fats generally known for use in the cosmetic arts.

Oils typically used in cosmetics include those selected from the group consisting of polar oils, non-polar oils, volatile oils, non-volatile oils and mixtures thereof. These oils may be saturated or unsaturated, straight or branched chained, aliphatic or aromatic hydrocarbons. Preferred oils include non-polar volatile hydrocarbons including isodecane (such as Permethyl-99A®, available from Presperse Inc.) and the C₇-C₈ through C₁₂-C₁₅ isoparaffins (such as the Isopar® Series available from Exxon Chemicals), as well as cyclomethicone (such as DC Fluids 244, 245, 344, 345).

Fats employed according to the invention are selected from the group consisting of fats derived from animals, vegetables, synthetically derived fats, and mixtures thereof wherein said fats have a melting point from about 55°C to about 100°C and a needle penetration, as measured according to the American standard ASTM D5, from about 3 to about 40 at 25°C. Preferably the fats selected for use in the present invention are fatty acid esters which are solids at room temperature and exhibit crystalline structure. Examples of fatty acid esters useful in the present invention include the glyceryl esters of higher fatty acids such as stearic and palmitic such as glyceryl monostearate, glyceryl distearate, glyceryl tristearate, palmitate esters of glycerol, C₁₈-36 triglycerides, glyceryl tribehenate and mixtures thereof.

B. Emulsifiers

A necessary components in the oil-in-water emulsion compositions of the present invention are emulsifiers. In these embodiments of the present invention, emulsifiers are typically used at levels from about 0.1% to about 40%, preferably from about 0.5% to about 30%.

There are many factors which determine whether the water or the oil end up the dispersed or continuous phase. However, the single most important factor is the hydrophilic-lipophilic balance value (herein referred to as HLB) of the emulsifier; Wilkinson and Moore, Harry's Cosmeticology, 7th Ed. 1982, p. 738. For example Schick and Fowkes, Surfactant Science Series, Vol. 2, Solvent Properties of Surfactant Solutions, p 607. Schick and Fowkes discloses that HLB values of surfactant emulsifiers for making oil-in-water emulsions is from 8-15. Said emulsifiers include those disclosed in

the C.T.F.A. Cosmetic Ingredient Handbook, 1992, pp.587-592; and Remington's Pharmaceutical Sciences, 15th Ed. 1975, pp 335-337; both incorporated herein by reference. Said emulsifiers are selected from those known in the art and mixtures thereof including those in McCutcheon's Volume 1, Emulsifiers & Detergents, 1994, North American Edition, pp. 236-239; herein incorporated by
5 reference.

C. Waxes

Waxes are defined as lower-melting organic mixtures or compounds of high molecular weight, solid at room temperature and generally similar in composition to fats and oils except that they contain no glycerides. Some are hydrocarbons, others are esters of fatty acids and alcohols. Waxes useful in
10 the present invention are selected from the group consisting of animal waxes, vegetable waxes, mineral waxes, various fractions of natural waxes, synthetic waxes, petroleum waxes, ethylenic polymers, hydrocarbon types such as Fischer-Tropsch waxes, silicone waxes, and mixtures thereof wherein the waxes have a melting point between 55° and 100°C and a needle penetration, as measured according to the American standard ASTM D5, of 3 to 40 at 25°C. The principle of the measurement of the needle
15 penetration according to the standards ASTM D5 consists in measuring the depth, expressed in tenths of a millimeter, to which a standard needle (weighing 2.5 g and placed in a needle holder weighing 47.5 g, i.e. a total of 50 g) penetrates when placed on the wax for 5 seconds. Waxes are used at levels in order to provide sufficient bulk material that resists drying out after application, providing thickness to the lashes. Levels of wax commonly found in the art are from about 1% to about 40%.

The specific waxes useful in the present invention are selected from the group consisting of beeswax, lanolin wax, shellac wax (animal waxes); carnauba, candelilla, bayberry (vegetable waxes); ozokerite, ceresin, (mineral waxes); paraffin, microcrystalline waxes (petroleum waxes); polyethylene, (ethylenic polymers); polyethylene homopolymers (Fischer-Tropsch waxes); C₂₄₋₄₅ alkyl methicones (silicone waxes); and mixtures thereof. Most preferred are beeswax, lanolin wax,
20 carnauba, candelilla, ozokerite, ceresin, paraffins, microcrystalline waxes, polyethylene, C₂₄₋₄₅ alkyl methicones, and mixtures thereof.

D. Pigments

The solids component of the mascara compositions of the present invention contain cosmetically acceptable pigments selected from the group consisting of inorganic pigments, organic
30 pigments, and pearlescent pigments. When employed, the pigments are present in proportions depending on the color and the intensity of the color which it is intended to produce. The level of pigments in the solid portion of the mascara composition of present invention is from about 3% to about 30%, preferably from about 5% to about 20%. Pigments are selected from the group consisting of inorganic pigments, organic lake pigments, pearlescent pigments, and mixtures thereof. Said
35 pigments may optionally be surface-treated within the scope of the present invention but are not limited to treatments such as silicones, perfluorinated compounds, lecithin, and amino acids.

Inorganic pigments useful in the present invention include those selected from the group

consisting of rutile or anatase titanium dioxide, coded in the Color Index under the reference CI 77,891; black, yellow, red and brown iron oxides, coded under references CI 77,499, 77, 492 and, 77,491; manganese violet (CI 77,742); ultramarine blue (CI 77,007); chromium oxide (CI 77,288); chromium hydrate (CI 77,289); and ferric blue (CI 77,510) and mixtures thereof.

- 5 The organic pigments and lakes useful in the present invention include those selected from the group consisting of D&C Red No. 19 (CI 45,170), D&C Red No. 9 (CI 15,585), D&C Red NO. 21 (CI 45,380), D&C Orange No. 4 (CI 15,510), D&C Orange No. 5 (CI 45,370), D&C Red No. 27 (CI 45,410), D&C Red No. 13 (CI 15,630), D&C Red No. 7 (CI 15,850), D&C Red No. 6 (CI 15,850), D&C Yellow No. 5 (CI 19,140), D&C Red No. 36 (CI 12,085), D&C Orange No. 10 (CI 45,425), D&C
10 Yellow No. 6 (CI 15,985), D&C Red No. 30 (CI 73,360), D&C Red No. 3 (CI 45,430) and the dye or lakes based on Cochineal Carmine (CI 75,570) and mixtures thereof.

- The pearlescent pigments useful in the present invention include those selected from the group consisting of the white pearlescent pigments such as mica coated with titanium oxide, bismuth oxychloride, colored pearlescent pigments such as titanium mica with iron oxides, titanium mica with
15 ferric blue, chromium oxide and the like, titanium mica with an organic pigment of the above-mentioned type as well as those based on bismuth oxychloride and mixtures thereof.

E. Miscellaneous

- In the present invention numerous optional ingredients may be added to provide additional benefits other than that attributed to the invention as defined above. For example, it is preferred that
20 the mascara composition of the present invention contain a preservative system to inhibit microbiological growth and maintain the integrity of the product. In the present invention, the preservative system does not have a detrimental effect on the composition.

- Any optional ingredients known to those skilled in the art may also be used in the invention. Examples of optional ingredients are cosmetic fillers including, but not limited to, mica, talc, nylon, polyethylene, silica, polymethacrylate, kaolin, teflon; cosmetic preservatives including, but not
25 limited to, methylparaben, propylparaben, butylparaben, ethylparaben, potassium sorbate, trisodium EDTA, phenoxyethanol, ethyl alcohol, diazolidinyl urea, benzyl alcohol, imidazolidinyl urea, quaternium-15. Also, additives such as tall oil glycerides are easily incorporated into emulsion forms of the mascara.

30

EXAMPLES

Example #1

<u>Ingredient</u>	<u>W/W%</u>
Deionized Water	49.96
Synthetic Wax	7.00
Glycerol Monostearate	3.00
Carnauba Wax	2.00
Black Iron Oxide	7.25

Quaternium-18 Hectorite ¹	4.00
Propylene Carbonate	1.33
Stearic Acid	2.75
Oleic Acid	0.75
Triethanolamine	1.75
Trisodium EDTA	0.10
Polyvinyl Alcohol	3.00
Propylene Glycol	2.00
Simethicone ²	0.20
Ammonium Acrylates Copolymer ³	12.20
Ethyl Alcohol ⁴	1.00
Benzyl Alcohol	0.65
Phenoxyethanol	0.28
Propylparaben	0.10
Methylparaben	0.20
Ethylparaben	0.20
Panthenol ⁵	0.28

1. available as Bentone 38 from Rheox.

2. available as Antifoam from Dow Corning.

3. available as Syntran EX33-1 (41% Stock Solution) from Interpolymer Corporation.

4. available as SD Alcohol 40-B from Warner Graham Company.

5 5. available as dl-Panthenol from Roche.

Example #2

Ingredient	W/W%
Deionized Water	40.18
Synthetic Wax	1.50
Glycerol Monostearate	7.25
Carnauba Wax	2.00
Black Iron Oxide	7.25
Quaternium-18 Hectorite ¹	3.75
Propylene Carbonate	1.25
Stearic Acid	2.75
Oleic Acid	1.00
Triethanolamine	1.75
Xanthan Gum	0.10
Trisodium EDTA	0.10

Polyvinyl Alcohol	1.50
Acrylates Copolymer ²	5.17
Propylene Glycol	2.00
Simethicone ³	0.20
Ammonium Acrylates Copolymer ⁴	18.29
Lecithin	1.25
Ethyl Alcohol ⁵	1.00
Benzyl Alcohol	0.65
Phenoxyethanol	0.28
Propylparaben	0.10
Methylparaben	0.20
Ethylparaben	0.20
Panthenol ⁶	0.28

1. available as Bentone 38 from Rheox.

2. available as Carboset xpd-1616 (29% Stock Soln) from BF Goodrich.

3. available as Antifoam from Dow Corning.

4. available as Syntran EX33-1 (41% Stock Solution) from Interpolymer Corporation.

5 5. available as SD Alcohol 40-B from Warner Graham Company.

6. available as dl-Panthenol from Roche.

Example #3

Ingredient	W/W%
Deionized Water	41.95
Synthetic Wax	3.00
Glycerol Monostearate	6.00
Carnauba Wax	4.50
Black Iron Oxide	7.25
Quaternium-18 Hectorite ¹	2.25
Propylene Carbonate	0.75
Stearic Acid	2.75
Oleic Acid	0.75
Triethanolamine	1.75
Trisodium EDTA	0.10
Polyvinyl Alcohol	4.00
Acrylates Copolymer ²	1.72
Propylene Glycol	2.00
Simethicone ³	0.20

Ammonium Acrylates Copolymer ⁴	17.07
Lecithin	1.25
Ethyl Alcohol ⁵	1.00
Benzyl Alcohol	0.65
Phenoxyethanol	0.28
Propylparaben	0.10
Methylparaben	0.20
Ethylparaben	0.20
Panthenol ⁶	0.28

1. available as Bentone 38 from Rheox.

2. available as Carboset xpd 1616 (29% Stock Soln) from BF Goodrich.

3. available as Antifoam from Dow Corning.

4. available as Syntran EX33-1 (41% Stock Solution) from Interpolymer Corporation.

5 5. available as SD Alcohol 40-B from Warner Graham Company.

6. available as dl-Panthenol from Roche.

Example #4

Ingredient	W/W%
Deionized Water	41.15
Synthetic Wax	4.00
Glycerol Monostearate	6.00
Carnauba Wax	3.75
Black Iron Oxide	9.00
Quaternium-18 Hectorite ¹	4.00
Propylene Carbonate	1.33
Stearic Acid	2.75
Oleic Acid	1.00
Triethanolamine	1.75
Trisodium EDTA	0.10
Propylene Glycol	1.00
Simethicone ²	0.20
Ammonium Acrylates Copolymer ³	19.51
Lecithin	1.75
Ethyl Alcohol ⁴	1.00
Benzyl Alcohol	0.65
Phenoxyethanol	0.28
Propylparaben	0.10

Methylparaben	0.20
Ethylparaben	0.20
Panthenol ⁵	0.28

1. available as Bentone 38 from Rheox.
2. available as Antifoam from Dow Corning.
3. available as Syntran EX33-1 (41% Stock Solution) from Interpolymer Corporation.
4. available as SD Alcohol 40-B from Warner Graham Company.
5. available as dl-Panthenol from Roche.

Example #5

Ingredient	W/W%
Deionized Water	37.43
Synthetic Wax	3.00
Glycerol Monostearate	7.00
Carnauba Wax	1.00
Black Iron Oxide	7.25
Quaternium-18 Hectorite ¹	3.75
Propylene Carbonate	1.25
Stearic Acid	2.75
Oleic Acid	0.75
Triethanolamine	1.75
Xanthan Gum	0.40
Trisodium EDTA	0.10
Polyvinyl Alcohol	1.00
Acrylates Copolymer ²	6.90
Propylene Glycol	2.00
Simethicone ³	0.20
Ammonium Acrylates Copolymer ⁴	19.51
Lecithin	1.25
Ethyl Alcohol ⁵	1.00
Benzyl Alcohol	0.65
Phenoxyethanol	0.28
Propylparaben	0.10
Methylparaben	0.20
Ethylparaben	0.20
Panthenol ⁶	0.28

1. available as Bentone 38 from Rheox.

2. available as Carboset xpd-1616 (29% Stock Soln) from BF Goodrich.
3. available as Antifoam from Dow Corning.
4. available as Syntran EX33-1 (41% Stock Solution) from Interpolymer Corporation.
5. available as SD Alcohol 40-B from Warner Graham Company.
- 5 6. available as dl-Panthenol from Roche.

Example #6

Ingredient	W/W%
Deionized Water	40.42
Synthetic Wax	3.00
Glycerol Monostearate	5.00
Carnauba Wax	1.00
Micronized Black	6.50
Quaternium-18 Hectorite ¹	6.00
Propylene Carbonate	2.00
Stearic Acid	2.75
Oleic Acid	1.00
Triethanolamine	1.75
Xanthan Gum	0.10
Trisodium EDTA	0.10
Polyvinyl Alcohol	1.00
Acrylates Copolymer ²	6.90
Propylene Glycol	1.00
Semithicone ³	0.20
Ammonium Acrylates Copolymer ⁴	17.07
Lecithin	1.50
Ethyl Alcohol ⁵	1.00
Benzyl Alcohol	0.65
Phenoxyethanol	0.28
Propylparaben	0.10
Methylparaben	0.20
Ethylparaben	0.20
Panthenol ⁶	0.28

1. available as Bentone 38 from Rheox.
2. available as Carboset xpd-1616 (29% Stock Soln) from BF Goodrich.
3. available as Antifoam from Dow Corning.
- 10 4. available as Syntran EX33-1 (41% Stock Solution) from Interpolymer Corporation.

5. available as SD Alcohol 40-B from Warner Graham Company.

6. available as dl-Panthenol from Roche.

Example #7

Ingredient	W/W%
Deionized Water	41.22
Synthetic Wax	5.00
Glycerol Monostearate	7.50
Carnauba Wax	2.75
Black Iron Oxide	7.50
Quaternium-18 Hectorite ¹	1.00
Propylene Carbonate	0.33
Stearic Acid	2.75
Oleic Acid	1.00
Triethanolamine	1.75
Xanthan Gum	0.40
Trisodium EDTA	0.10
Polyvinyl Alcohol	4.00
Acrylates Copolymer ²	1.72
Propylene Glycol	2.00
Antifoam	0.20
Ammonium Acrylates Copolymer ³	17.07
Lecithin	1.00
Ethyl Alcohol ⁴	1.00
Benzyl Alcohol	0.65
Phenoxyethanol	0.28
Propylparaben	0.10
Methylparaben	0.20
Ethylparaben	0.20
Panthenol ⁵	0.28

1. available as Bentone 38 from Rheox.

5 2. available as Antifoam from Dow Corning.

3. available as Syntran EX33-1 (41% Stock Solution) from Interpolymer Corporation.

4. available as SD Alcohol 40-B from Warner Graham Company.

5. available as dl-Panthenol from Roche.

Example #8

Ingredient	W/W%
------------	------

Deionized Water	41.18
Synthetic Wax	1.50
Glycerol Monostearate	6.50
Carnauba Wax	2.75
Black Iron Oxide	7.25
Quaternium-18 Hectorite ¹	4.00
Propylene Carbonate	1.33
Stearic Acid	2.75
Oleic Acid	1.00
Triethanolamine	1.75
Trisodium EDTA	0.10
Polyvinyl Alcohol	2.50
Acrylates Copolymer ²	1.72
Propylene Glycol	2.00
Semithicone ³	0.20
Ammonium Acrylates Copolymer ⁴	19.51
Lecithin	1.25
Ethyl Alcohol ⁵	1.00
Benzyl Alcohol	0.65
Phenoxyethanol	0.28
Propylparaben	0.10
Methylparaben	0.20
Ethylparaben	0.20
Panthenol ⁶	0.28

1. available as Bentone 38 from Rheox.

2. available as Carboset xpd-1616 (29% Stock Soln) from BF Goodrich.

3. available as Antifoam from Dow Corning.

4. available as Syntran EX33-1 (41% Stock Solution) from Interpolymer Corporation.

5 5. available as SD Alcohol 40-B from Warner Graham Company.

6. available as dl-Panthenol from Roche.

Example #9

Ingredient	W/W%
Deionized Water	41.88
Synthetic Wax	2.00
Glycerol Monostearate	5.25
Carnauba Wax	3.00

Black Iron Oxide	7.25
Quaternium-18 Hectorite ¹	4.00
Propylene Carbonate	1.33
Stearic Acid	2.75
Oleic Acid	0.80
Triethanolamine	1.75
Trisodium EDTA	0.10
Polyvinyl Alcohol	2.50
Acrylates Copolymer ²	1.72
Propylene Glycol	2.00
Semithicone ³	0.20
Ammonium Acrylates Copolymer ⁴	19.51
Lecithin	1.25
Ethyl Alcohol ⁵	1.00
Benzyl Alcohol	0.65
Phenoxyethanol	0.28
Propylparaben	0.10
Methylparaben	0.20
Ethylparaben	0.20
Panthenol ⁶	0.28

1. available as Bentone 38 from Rheox.

2. available as Carboset xpd-1616 (29% Stock Soln) from BF Goodrich.

3. available as Antifoam from Dow Corning.

4. available as Syntran EX33-1 (41% Stock Solution) from Interpolymer Corporation.

5 5. available as SD Alcohol 40-B from Warner Graham Company.

6. available as dl-Panthenol from Roche.

PROCESSING DIRECTIONS

- 10 Place the waxes and fats into a vessel equipped with heating and mixing. Heat the waxes and fats to about 90- 95°C with low speed mixing until liquefied and homogeneous. Add oil-dispersible or oil-soluble components such as pigments and organophilic clays and clay activators. Increase the mixing rate to high and mix until the pigments are uniformly dispersed throughout the lipid mixture; about 30-35 minutes. Add emulsifiers to said lipid mixture while continuing to mix .
- 15 In a second vessel equipped with mixing and heating, add water followed by the water-soluble, film-forming polymers, and the remainder of the water-dispersible components. The mixture of water and water-soluble film forming polymers can be made up ahead of the processing of the

mascara composition. Mix with heating until this aqueous mixture is about 90- 95°C. Q.S. for any water loss from said aqueous mixture.

- 5 Slowly combine the two mixtures and mix with a high speed dispersator type mixer. Remove heat source and continue mixing this combined mixture until the temperature of said combined mixture is from about 65°C-70°C. Q.S. said combined mixture for any water loss, add the preservatives and insoluble polymer component and mix until homogeneous. Cool said combined mixture to about 45-47°C. Add any remaining components. Continue cooling and mixing until said combined mixture is about 27- 30°C. Transfer said combined mixture to suitable storage containers for subsequent filling of retail size packaging.

WHAT IS CLAIMED IS:

1. A cosmetic composition in the form of an oil-in-water emulsion comprising water-insoluble polymeric materials, water-soluble film-forming polymers and organophilic clays.
2. A cosmetic composition according to Claim 1 comprising :
 - a. from 3% to 60%, preferably 4% to 40%, and most preferably 5% to 30% of a water-insoluble polymeric material, preferably incorporated into said composition in the form of an aqueous emulsion;
 - b. from 0.1% to 50%, preferably 1% to 30%, most preferably 1.5% to 10% of a water-soluble, film-forming polymer; and
 - c. from 0.05% to 20.0%, preferably 1% to 10%, most preferably 2% to 5% of an organophilic clay.
3. A mascara composition according to Claim 1 or Claim 2 wherein:
 - a. both said water-insoluble polymeric material and said water-soluble film-forming material comprises polymers formed from monomers, derivatives of said monomers, mixtures of said monomers and derivatives, natural polymers and mixtures thereof; and
 - b. said organophilic clay is selected from the group consisting of organically-modified montmorillonite, bentonite, hectorite, attapulgite, sepiolite and mixtures thereof.
4. A mascara composition according to any of Claims 1 to 3 wherein said water-insoluble polymeric material comprises monomers and monomer derivatives selected from the group consisting of aromatic vinyls, dienes, vinyl cyanides, vinyl halides, vinylidene halides, vinyl esters, olefins and their isomers, vinyl pyrrolidone, unsaturated carboxylic acids, alkyl esters of unsaturated carboxylic acids, hydroxy derivatives of alkyl esters of unsaturated carboxylic acids, amides of unsaturated carboxylic acids, amine derivatives of unsaturated carboxylic acids, glycidyl derivatives of alkyl esters of unsaturated carboxylic acids, olefinic diamines and isomers, aromatic diamines, terephthaloyl halides, olefinic polyols, and mixtures thereof; preferably selected from the group consisting of aromatic vinyls, dienes, vinyl esters, olefins and their isomers, unsaturated carboxylic acids, alkyl esters of unsaturated carboxylic acids, hydroxy derivatives of alkyl esters of unsaturated carboxylic acids, amides of unsaturated carboxylic acids and mixtures thereof; most preferably selected from the group consisting of aromatic vinyls, dienes, vinyl esters, alkyl esters of unsaturated carboxylic acids, hydroxy derivatives of alkyl esters of unsaturated carboxylic acids and mixtures thereof.
5. A mascara composition according to any of Claims 1 to 4 wherein the water-soluble, film-forming polymeric material comprises monomers and monomer derivatives selected from the

group consisting of olefin oxides, vinyl pyrrolidone, vinyl esters, vinyl alcohols, vinyl cyanides, oxazolines, carboxylic acids and esters and mixtures thereof.

6. A mascara composition according to any of Claims 1 to 5 wherein said water-soluble film-forming polymeric material comprises vinyl pyrrolidone polymers selected from polyvinylpyrrolidone, vinyl acetate/vinyl pyrrolidone copolymers and mixtures thereof; vinyl ester polymers selected from vinyl acetate/crotonic acid copolymer, vinyl acetate/crotonic acid/vinyl neodecanoate copolymer and mixtures thereof; vinyl alcohol polymers selected from vinyl alcohol/vinyl acetate, vinyl alcohol/poly(alkyleneoxy)acrylate and mixtures thereof; olefin oxide polymers selected from polyethylene oxide, polypropylene oxide and mixtures thereof; carboxylic acid and ester polymers selected from acrylates, acrylate/octyl-acrylamide copolymers and mixtures thereof; or polyoxazilines.
7. A mascara composition according to any of Claims 1 to 6 wherein the natural polymers are selected from the group consisting of cellulose derivatives, preferably hydroxyethylcellulose, hydroxypropylcellulose, hydroxypropyl methylcellulose, ethylhydroxyethyl cellulose and mixtures thereof; algin and its derivatives; starch and its derivatives; guar and its derivatives; shellac polymers; and mixtures thereof.
8. A mascara composition according to any of Claims 1 to 7 wherein the organophilic clay is organically-modified bentonite.
9. A mascara composition according to any of Claims 1 to 8 wherein the clay is incorporated into the oil phase of the oil-in-water emulsion.
10. A process for making a mascara composition wherein organophilic clays are incorporated into an oil-in-water emulsion to form said composition.

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 6 : A61K 7/032	A3	(11) International Publication Number: WO 98/18431 (43) International Publication Date: 7 May 1998 (07.05.98)
(21) International Application Number: PCT/US97/19786 (22) International Filing Date: 30 October 1997 (30.10.97) (30) Priority Data: 08/740,578 31 October 1996 (31.10.96) US (71) Applicant: THE PROCTER & GAMBLE COMPANY [US/US]; One Procter & Gamble Plaza, Cincinnati, OH 45202 (US). (72) Inventors: ALWATTAL, Ali, Abdelaziz; 9325 Winton Road #7, Cincinnati, OH 45231 (US). BARTHOLOMEY, Ed- ward, Martin; 9031 Fieldchat Road, Baltimore, MD 21236 (US). SMITH, Edward, Dewey, III; 6880 Man-O-War Lane, Mason, OH 45040 (US). TARANTINO, David, Ed- mund; 4 Rainflower Path #304, Sparks, MD 21152 (US). WALLING, David, William; 2 Andrews Court, Parkton, MD 21120 (US). (74) Agents: REED, T., David et al.; The Procter & Gamble Company, 5299 Spring Grove Avenue, Cincinnati, OH 45217 (US).		(81) Designated States: AU, CA, CN, CZ, JP, MX, European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i> (88) Date of publication of the international search report: 23 July 1998 (23.07.98)
(54) Title: COSMETIC COMPOSITIONS COMPRISING AN INSOLUBLE POLYMER, A FILM-FORMING POLYMER AND AN ORGANOPHILIC CLAY (57) Abstract The present invention relates to oil-in-water mascara compositions comprising water-insoluble polymeric materials in the form of an aqueous emulsion, water-soluble, film-forming polymers and organophilic clays. Said compositions exhibit improved wear and are removable with soap and water.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon		Republic of Korea	PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 97/19786

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 A61K7/032

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 6 A61K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 4 917 883 A (STROBRIDGE JOHN R) 17 April 1990 see column 2, line 65 - column 4, line 43 see column 5, line 60 - column 6, line 10 ---	1
P,X	WO 96 33690 A (PROCTER & GAMBLE) 31 October 1996 see claims; examples 1,2 see page 8, line 18 - line 26 ---	1-10
P,X	WO 96 36308 A (PROCTER & GAMBLE ;MCDERMOTT PADRAIG HUGH (GB)) 21 November 1996 see page 11, line 20 - page 12, line 21 ---	10
A	WO 91 12793 A (L'OREAL) 5 September 1991 cited in the application see claims 1,2; examples ---	1,3,5,10
-/-		

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

A document defining the general state of the art which is not considered to be of particular relevance

E earlier document but published on or after the international filing date

L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

O document referring to an oral disclosure, use, exhibition or other means

P document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

& document member of the same patent family

Date of the actual completion of the international search

20 April 1998

Date of mailing of the international search report

27.05.98

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

McConnell, C

INTERNATIONAL SEARCH REPORT

Intern. Application No
PCT/US 97/19786

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	GB 2 238 242 A (MAYBE HOLDING CO) 29 May 1991 see page 1, line 23 - line 34 see page 11, line 25; table 2 ---	1,4,5,10
A	WO 93 16684 A (L'OREAL) 2 September 1993 see examples D,F,G see page 4, line 34 - page 5, line 22 ---	1,2,5-8
A	PATENT ABSTRACTS OF JAPAN vol. 096, no. 008, 30 August 1996 & JP 08 084921 A (MIKIMOTO PHARMACEUT CO LTD), 2 April 1996, see abstract ---	1,3,5
A	PATENT ABSTRACTS OF JAPAN vol. 096, no. 012, 26 December 1996 & JP 08 217619 A (SHISEIDO CO LTD), 27 August 1996, see abstract ---	1,3,4
A	WO 92 19215 A (PROCTER & GAMBLE) 12 November 1992 see page 2, line 8 - page 4, line 27 -----	1,10

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 97/19786

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 4917883 A	17-04-90	AU 618876 B AU 4998790 A US 5041281 A	09-01-92 20-09-90 20-08-91
WO 9633690 A	31-10-96	AU 5374396 A EP 0824339 A	18-11-96 25-02-98
WO 9636308 A	21-11-96	EP 0827388 A	11-03-98
WO 9112793 A	05-09-91	FR 2659011 A AU 635630 B AU 7452491 A CA 2046600 A DE 69101889 D DE 69101889 T EP 0471054 A ES 2052376 T JP 2623168 B JP 4505469 T	06-09-91 25-03-93 18-09-91 02-09-91 09-06-94 22-12-94 19-02-92 01-07-94 25-06-97 24-09-92
GB 2238242 A	29-05-91	US 5053221 A CA 2030289 A JP 3209308 A MX 172080 B	01-10-91 21-05-91 12-09-91 01-12-93
WO 9316684 A	02-09-93	FR 2687932 A AT 135564 T CA 2109195 A DE 69301877 D DE 69301877 T EP 0583459 A ES 2086935 T JP 6507422 T	03-09-93 15-04-96 28-08-93 25-04-96 10-10-96 23-02-94 01-07-96 25-08-94
WO 9219215 A	12-11-92	AU 2002592 A MX 9201926 A	21-12-92 01-11-92

THIS PAGE BLANK (USPTO)